



ST-15

1 HOUR FIRE ASSEMBLY- MEDIUM WEIGHT STRUCTURAL STEEL BEAM

TYPICAL ASSEMBLY - MEDIUM WEIGHT STRUCTURAL STEEL MEMBER USED HORIZONTALLY AS A BEAM OR 45 DEG BRACING

Medium weight defined as 10 LBS-23.9 LBS. per liner foot of material



**TO ACHIEVE 1 HOUR RATING:
 PREPARATION OF STEEL MEMBER: CLEAN AND APPLY COMPATIBLE STEEL PRIMER @ 2.5 MIL.
 APPLY 30 MIL THICKNESSES (DRY) OF ForceField® FireGuard® E-84 TO ALL EXPOSED SIDES OF STEEL BEAM.**



30 MIL THICKNESS (DRY) OF FFG E-84 INTUMESCENT COATING

SCALE: N.T.S.

FIRE TEST ENDURANCE RATING:	1 HOUR
STANDARD TESTED TO:	ASTM E-119-11A STRUCTUAL STEEL SECTION; NFPA 251; UL 263; ULC S-101-07 WITH NO LOAD CAPACITY, NO RESTRAINT, SMALL SCALE TEST
FIRE TESTED LABORATORY	GUARDIAN FIRE LABORATORIES, INC. 480 HINMAN AVE. BUFFALO, NY 14216
REPORT NO:	GL 88311
PRODUCT:	ForceField® FireGuard E-84® INTUMESCENT COATING (FFG E-84)
MANUFACTURER:	SHIELD INDUSTRIES, INC. 131 SMOKEHILL LANE WOODSTOCK, GA 30188
*SEE MANUFACTURER APPLICATION INSTRUCTIONS AND SPECIFICATIONS FOR SURFACE PREPARATION AND APPLICATION PROCESS	

GUARDIAN
R. Joseph Pearson
 5/20/14



Laura Ann Hinton 5/19/2014