







## TO ACHIEVE 20 MINUTES FIRE RATING:

PREPERATION OF DOOR ASSEMBLY: CLEAN AND APPLY PRIMER @ 2.5 MILS.

APPLY 25 MIL THICKNESS (DRY) OF ForceField® FireGuard® E-84 TO ALL EXPOSED SIDES OF METAL FRAME & WOOD DOOR ASSEMBLY

SCALE: N.T.S.

FIRE TEST ENDURANCE RATING:	20 MINUTES
STANDARD TESTED TO:	UL 10B, NFPA 252
FIRE TESTED LABORATORY:	GUARDIAN FIRE TESTING LABORITORIES, INC. 480 HINMAN AVE.
	BUFFALO, NY 14216
REPORT NO:	GL78413
PRODUCT:	ForceField® FireGuard® E-84 INTUMESCENT COATING (FFG E-84)
	<u> </u>
MANUFACTURER:	SHIELD INDUSTRIES, INC. 131 SMOKEHILL LANE
	WOODSTOCK, GA 30188
* SEE MANUFACTURER APPLICATION INSTRUCTIONS AND SPECIFICATIONS FOR SURFACE PREPARATION AND APPLICATION PROCESS	
SON ACE THE ANATION AND ATTECATION PROCESS	