



ST-20

90 Min FIRE ASSEMBLY - LIGHT WEIGHT STRUCTURAL STEEL COLUMN

TYPICAL ASSEMBLY - LIGHT WEIGHT STRUCTURAL STEEL MEMBER USED VERTICALLY AS A COLUMN

Light weight defined as 1 LBS-9.9LBS. per liner foot of material



**TO ACHIEVE 90 MIN RATING (USING CRITERIA 1300 ° F AVERAGE):
 PREPARATION OF STEEL MEMBER: CLEAN AND APPLY COMPATIBLE STEEL PRIMER @ 2.5 MIL.
 APPLY 60 MIL THICKNESSES (DRY) OF ForceField® FireGuard® E-84 TO ALL EXPOSED SIDES OF STEEL COLUMN.**



60 MIL THICKNESS (DRY) OF FFG E-84 INTUMESCENT COATING

SCALE: N.T.S.



FIRE TEST ENDURANCE RATING:	90 MIN
STANDARD TESTED TO:	ASTM E-119-11A STRUCTURAL STEEL SECTION; NFPA 251; UL 263; ULC S-101-07 WITH NO LOAD CAPACITY, NO RESTRAINT, SMALL SCALE TEST
FIRE TESTED LABORATORY	GUARDIAN FIRE LABORATORIES, INC. 480 HINMAN AVE. BUFFALO, NY 14216
REPORT NO:	GL 115611
PRODUCT:	ForceField® FireGuard E-84® INTUMESCENT COATING (FFG E-84)
MANUFACTURER:	SHIELD INDUSTRIES, INC. 131 SMOKEHILL LANE WOODSTOCK, GA 30188
*SEE MANUFACTURER APPLICATION INSTRUCTIONS AND SPECIFICATIONS FOR SURFACE PREPARATION AND APPLICATION PROCESS	



Laura Ann Hinton 5/19/2014